



Micronized Carbon Black Data sheet							
Test Name Pigment Grade	Particle Size	Mesh	Ash content	Heat Loss	tint Strength	iodine adsorption number	DBP Absorption Number
940-50	<1 µm	>5000	<0.70	2.0	59-69	47	117-127
940-70	<1 µm	>5000	<0.70	2.0	120-130	122	119-129
P940-30	<1 µm	>5000	<0.70	2.0	99-109	87	99-109
P940-20	<1 µm	>5000	<0.70	2.0	109-119	126	111-121
P940-10	<1 µm	>5000	<0.70	2.0	108-118	95	118-128
P940-08	<1 µm	>5000	2.0	1.74	95-105	89	111-121
P940-05	<1 µm	>5000	4.0	1.36	81-91	80	98-108
P940-02	<1 µm	>5000	8.2	0.97	56-66	71	89-99
P940	<1 µm	>5000	10.0	0.72	42-52	65	83-93
Black Filler	5-10 µm	>2500	10.5	0.70	-	-	-

www.goharfarayand.com

E-mail: gohar.farayand@yahoo.com

آدرس: اصفهان، خ ابوزر، خ 23، پ 7 کدپستی:

Add: No. 7, 23rd St. Abuzar Ave., Esfahan, Esfahan,
Iran

تلفن: 09133679100 همراه: 031-46412867

Tel: +98(311)235-7242 Cell phone: +98 913 367 9100

